

	DecoFilm Paint FX	DecoFilm	DecoSparkle	DecoFlock	GlitterFlex II	GlitterFlex Ultra	Crazy Crystal Colors	ThermoFlex Xtra	ThermoFlex Plus	ThermoFlex Sport	FashionFlex	ColorJet III Dark	Wild Fashion Prints
Blade	Standard blade	Standard for Supers. Thick for Brilliants with high pressure.	Standard with high pressure	Thick materials blade	Thick materials blade	Thick materials blade	Thick materials blade	Standard blade	Standard blade	Standard blade	Standard blade	Standard blade	Standard blade
Fabric	Most fabrics. No nylon.	Cotton, Polyester, fabric blends, wool. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.	Cotton, Polyester, fabric blends, wool, linen. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.	Cotton, Polyester, fabric blends, spandex, lycra, wool, linen. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.	Cotton, Polyester, fabric blends, spandex, lycra, wool, linen. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.	Cotton, Polyester, fabric blends, spandex, lycra, wool, linen. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.	Cotton, Polyester, fabric blends, wool, linen. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials. DO NOT PRESS TWICE, or it loses its gloss effect.	Nylon, leather, and other heat sensitive fabrics. Moisture-wicking material should be rubbed with a cloth dampened with rubbing alcohol and allowed to dry before applying. Dazzle cloth and shiny polyesters must be washed before applying.	Cotton, Polyester, Cotton/Polyester, Polyester/Acrylic. Moisture-wicking material should be rubbed with a cloth dampened with rubbing alcohol and allowed to dry before applying. Dazzle cloth and shiny polyesters must be washed before applying.	Cotton, polyester, mesh, poly-blend fabrics. Moisture-wicking material should be rubbed with a cloth dampened with rubbing alcohol and allowed to dry before applying. Dazzle cloth and shiny polyesters must be washed before applying.	Cotton, polyester, fabric blends, spandex, lycra, wool, linen. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.	Cotton and blended fabrics. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.	Cotton, Polyester, fabric blends, spandex, lycra, wool, linen. No nylon, dazzle cloth, shiny polyester, or moisture-wicking materials.
Image	Cut mirror image.	Cut mirror image.	Cut mirror image.	Cut mirror image.	Remove heat liner. Cut mirror image.	Cut mirror image.	Cut mirror image.	Cut mirror image.	Cut mirror image.	Cut mirror image.	Cut mirror image.	Cut material "right". Use heat transfer material to apply to fabric.	Cut mirror image.
Pressure	Firm, even pressure. Cover and reheat if necessary.	Firm, even pressure. Cover and reheat if necessary.	Medium to Firm, even pressure	Medium to Firm, even pressure	Firm, even pressure	Firm, even pressure	Firm to hard, even pressure.	Firm to hard, even pressure.	Medium to Firm, even pressure.	Medium, even pressure.	Firm, even pressure	Medium to Firm, even pressure.	Firm, even pressure
Temperature	310°F - 330°F (154°C-165°C)	310°F - 330°F (154°C-165°C)	300°F (149°C)	320°F - 340°F (160°C-171°C)	330°F - 335°F (165°C-168°C)	330°F - 335°F (165°C-168°C)	340°F - 350°F (171°C-177°C)	310°F - 315°F (154°C-157°C)	330°F - 335°F (165°C-168°C)	300°F - 320°F (149°C-160°C)	315°F - 330°F (157°C-165°C)	340°F - 350°F (171°C-177°C)	325°F - 340°F (163°C-171°C)
Time	17-20 seconds	10-15 seconds	10-12 seconds	10-15 seconds	3 seconds	17-20 seconds	15-20 seconds	3-5 seconds	17-20 seconds	8-10 seconds	17-20 seconds	15-20 seconds	12-15 seconds
Peel	Peel Warm	Peel Cold	Peel Cold	Peel Cold	Peel warm, cover with Teflon sheet, repress for 10 seconds	Peel warm, cover with Teflon sheet, repress for 10 seconds	Peel Cold	Peel warm, cover with Teflon sheet, repress for 10 seconds	Peel warm. For neons and Columbia Blue PEEL COLD.	Peel warm or cold	Peel warm, repress for 2 seconds.	Peel cold	Peel cold
Wash/Dry	Wash inside out, cold water, gentle cycle. Dry low heat.	Super Silver, Gold, and Copper - Wash inside out, gentle cycle, cold water, tumble dry low heat. Suitable for dry cleaning. All others - hand wash only.	Wash inside out, gentle cycle, cold water, tumble dry low heat. Suitable for dry cleaning. All others - hand wash only.	Can be washed and dried at medium temperatures.	Wash inside out, cold water, gentle cycle, tumble dry low heat.	Wash inside out, cool water, tumble dry low heat.	Cold water, gentle cycle, tumble dry low heat.	Follow wash instructions for nylon. Turn inside-out, cold water, tumble dry low heat. Suitable for dry cleaning.	Wash warm, tumble dry normal. Suitable for dry cleaning.	Wash with normal settings.	Wash inside out, wash cool, tumble dry low heat.	Wash inside out, gentle cycle, cold water, tumble dry low heat.	Cold water, gentle cycle, tumble dry low heat.